Autex Acoustics [®]	Cube™	Data Sheet		
Product overview	•	h Print, Mould & Press, Precision		
Sustainable material	 Carbon neutral product Zero carbon manufacturing Recycled content >60% recycled material 	 Low VOC and CDPH compliant <0.092 mg/m3 (7 days) Zero waste manufacturing initiative Sustainable supply chain and anti-modern slavery 		
Environmental certifications	 EPD – compliant with ISO 14025 and ISO 15804 Declare – Red List free (third party verified) 	 ISO 14001 Certified Environmental Management Health Product Declaration CDPH Standard 		
	Red List Free List Free Declar			
Certifying your green building		/ELL, LEED, Green Star, and BREEAM building tion for your project. For support and guidance t www.autexglobal.com, or speak with your		
Specification	(Wall) treatment shall be Cube™ from thermally bonded high density polyester containing not less than 60% recycled material as manufactured by Autex www.autexglobal.com	– with 24 mm air gap: Class C, NRC 0.80. Fire rating ASTM E-84-15a: Class A, FS:0 - SD:45, ISO 9705: Classification: Group 1-S, AS ISO 9705 – 2003 Classification: Group 1, 12 mm BS EN 13501-1:2018: B - s2, d0,		
	Panel 1220 x 2440 x (_)mm (nom.) depth, colour (_), sound absorption 12 mm: Class D, NRC 0.45 – with 24 mm air gap: Class C, NRC 0.70. 24 mm: Class D, NRC 0.70	24 mm BS EN 13501-1:2018: B - s2, d2. If Cube is to be specified for use other than as a wallcovering, please seek guidance from your account manager		

Product specifications

Product name	Cube™		
Composition 100% pol			
Panel dimensions	1220 mm x 24		
Tolerance	(+ 5 mm) x (+		
Thickness	12 mm 24		
Tolerance	(+/- 6%) (+/		

ster fibre 2440 mm + 10 mm) mm /- 6%)

Thermal performance

(Internally tested by Autex Lab)	
Cube 12 mm	R0.41 (@15°C)
Cube 24 mm	R0.82 (@15°C)

Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack or available on the website. If Cube is to be specified for use other than as a wallcovering, please seek guidance from your account manager.



Product specifications

Fire ratings Cube has been evaluated using the following test methods

ISO 9705: 1993

Classification: Group 1-S Smoke production rate: <5.0m2/s As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1 (SMOGRArc): <100m2/s2 Assessed using methodology A5 ISO 9705 - 2003 in accordance with A5 65712015, as required by BCA Specification C1:0-4 FI 4974 EAR 4055

BS EN 13501-1:2018

Wall applications Classification: B-s2,d0 (Cube[™] 12 mm) Tested using BS EN ISO 11925-22020 and BS EN 138232020 and classified in accordance with BS EN 13501-12018, as required by BS EN 151022007 + A12011. EUI-20-000268-A

Ceiling applications Classification: B-s2,d0 (Cube™ 12 mm) Tested using BS EN ISO 11925-22020 and BS EN 138232020 and classified in accordance with BS

EN 13501-1:2018, as required by BS EN 13964:2014. EUI-20-000268-B

Wall applications Classification: B-s2,d2

(Cube™ 24 mm) Tested using BS EN ISO 11925-22020 and BS EN 138232020 and classified in accordance with BS EN 13501-12018, as required by BS EN 15102-2007 + A12011. EUI-21-000135-G-A Ceiling applications Classification: B-s2,d2 (Cube™ 24 mm) Tested using BS EN ISO 11925-22020 and BS EN 13823-2020 and classified in accordance with BS EN 13501-12018, as required by BS EN 13964-2014. EUI-21-000135-G-B

ASTM E-84-15a

Class A, FS:0 - SD:45 (Cube™ 1/2") ^{RJ479-2} Class A, FS:0 - SD:65 (Cube™ 1") RJ479-1

Water vapour sorption

ASTM C1104 / C1104M-13a Test conditions: 49°C, 95%RH Water vapour absorbed and adsorped after 4 days: 0.4% by weight

Impact resistance ISO 7892:1988

Hard body impact

There is no surface damage or penetration to Cube when subjected to hard body impacts. When adhered to 10 mm plasterboard, the system can resist a 9 joule impact. This is equivalent to the impact of a 0.5 kg object dropped from a 2 m height. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5 kg object dropped from a 0.5 m height.

Soft body impact

There is no surface damage or penetration to Cube when subjected to soft body impacts. When adhered to 10 mm plasterboard, the system can resist a 70 joule impact. This is equivalent to the impact of a 50 kg object dropped from a 150 mm height.

Microbial resistance

ASTM G21-15 Growth rating: 0 (No growth) Cube does not promote the growth of moulds and mildew.

Colour fastness to light

Cube is suitable for indoor use only. Light fastness is dependent on use and exposure. Cube has been evaluated to the following standard: ISO 105-B02:2014 Rating: 6 (Highest = 7)

Colour fastness to rubbing

ISO 105-X12:2016 Dry rating: 4-5 (Highest = 5) Wet rating: 4-5 (Highest = 5)

Pattern repeat

Non-woven. No pattern repeat but product has directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed.

Blot with a clean dry cloth after each application of solution. Custom printed Cube requires the services of a specialist cleaning company. Refer to the Cube Care and Maintenance Guide for more information.

Service

For further information about Cube or any other Autex Acoustics product, please contact your account manager or visit our website.

Acoustic performance


Cube is specifically designed to reduce and control reverberated and echo noise in building interiors.

	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
•	12 mm Cube	0.05	0.10	0.30	0.65	0.90	0.95	0.45
•	12 mm Cube (with 25 mm air gap)	0.05	0.30	0.60	0.95	0.95	0.85	0.70
•	24 mm Cube	0.05	0.20	0.60	0.90	1.00	1.00	0.70
•	24 mm Cube (with 25 mm air gap)	0.15	0.40	0.85	0.95	0.95	0.95	0.80

Graph presents third octave sound absorption coefficients (according to ISO 354 measurement of sound absorption in a reverberation room). The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centred on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz and rounded to the nearest 0.05.

Absorption Coefficient According to ISO 354 University of Auckland Testing Service

Cube (12 mm) - Test No. T0712-3 Cube (12 mm with 25 mm air gap) - Test No. T0712-6 Cube (24 mm) - Test No. T1961-1 Cube (24 mm with 25 mm air gap) - Test No. T1326-2





Light reflectance values by colour

Cube is suitable for indoor use only. LRVs were measured in accordance with BS 8493:2008+A1:2010

Pavilion	80
Opera	49
Savoye	46
Rosada	45
Senado	44
Acros	40
Falling Water	34
Parthenon	33
Beehive	33
Bosco	29
Flatiron	24
Zenith	23

15
14
13
12
9
8
5
4
3
3
2

Autex Industries Ltd

702-718 Rosebank Rd Private Bag 19988 Avondale 1746, Auckland New Zealand Freephone 0800 428 839 Phone +64 9 828 9179 Fax +64 9 828 5810

• Autex Australia Pty Ltd

166 Bamfield Road PO Box 5099 West Heidelberg, Melbourne VIC 3081, Australia Freephone 1800 678 160 Phone +61 3 9457 6700 Fax +61 3 9457 1020

Autex Acoustics Ltd

Unit J4, Lowfields Way, Lowfields Business Park, Elland, West Yorkshire Hx5 9Da United Kingdom Phone +44 0 1422418899

Autex Acoustics LLC

1630 Dan Kipper Dr, Riverside, CA 92507 United States of America Phone +1 424 203 1813

An ISO 9001, ISO 14001 and ISO 45001 certified company. The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2021 Autex Industries Ltd. All Rights Reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.